

# Application / Specification Data for Tungsten ToolWorks' Series Reamers

Spiral flutes produce the best hole finish. Right-hand spiral should be used for blind holes, while left-hand spiral is excellent for thru-hole applications. Straight flute is appropriate for all general reaming requirements. Carbide reamers constructed with steel shank are induction-brazed (using controlled-frequency amplification) and slow-cooled in our own factory for maximum strength. All products are manufactured with centers (male, female, or both) for high concentricity characteristics and resharp capabilities. Also, shanks are ground to the next smallest common fractional diameter for effective tool-holding and practicality.

Material	SFPM	SFPM	1/16"	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	5/8"	3/4"
<b>Steel</b>	Uncoated	SmoothCoat	Feed Rate: Inches Per Rev (IPR)									
1018 / 1020	50 to 125	50 to 150	.0040	.0050	.0050	.0060	.0070	.0080	.0090	.0100	.0100	.0100
4140 / 4340 / P20	40 to 120	40 to 140	.0040	.0040	.0040	.0040	.0050	.0050	.0050	.0060	.0060	.0060
<b>Stainless Steel</b>												
303 / 304 / 316	30 to 120	30 to 140	.0040	.0050	.0050	.0060	.0070	.0080	.0090	.0100	.0100	.0100
410 / 420 / 440C	20 to 80	20 to 100	.0040	.0050	.0050	.0060	.0070	.0080	.0090	.0100	.0100	.0120
15-5/17-4 ≤ 32HRc	40 to 140	40 to 160	.0040	.0040	.0040	.0040	.0050	.0050	.0050	.0060	.0070	.0080
15-5/17-4 ≥ 32HRc	25 to 100	25 to 120	.0020	.0020	.0030	.0030	.0040	.0040	.0050	.0050	.0060	.0060
13-8 / 316L	30 to 120	30 to 140	.0040	.0050	.0050	.0060	.0070	.0080	.0090	.0100	.0100	.0100
<b>Tool Steel</b>												
A2/D2/H13 ≤ 32HRc	30 to 120	30 to 120	.0040	.0040	.0040	.0040	.0050	.0050	.0050	.0060	.0070	.0080
A2/D2/H13 ≥ 32HRc	20 to 80	20 to 100	.0020	.0020	.0030	.0030	.0040	.0040	.0050	.0050	.0060	.0060
<b>Titanium</b>												
6Al-4V	20 to 100	20 to 120	.0020	.0020	.0030	.0030	.0040	.0040	.0060	.0060	.0080	.0100
<b>High Temp Alloys</b>												
Inconel 625	20 to 60	20 to 80	.0020	.0020	.0030	.0030	.0040	.0040	.0050	.0050	.0060	.0060
Inconel 718	20 to 50	20 to 70	.0020	.0020	.0030	.0030	.0040	.0040	.0050	.0050	.0060	.0060
<b>Cast Iron</b>												
Gray Iron ≤ 32HRc	80 to 200	80 to 250	.0060	.0060	.0060	.0060	.0070	.0080	.0100	.0120	.0140	.0150
Ductile Iron	80 to 200	80 to 250	.0060	.0060	.0060	.0060	.0070	.0080	.0100	.0100	.0100	.0120
<b>Non-Ferrous</b>												
6061 T6 Aluminum	100 to 300	100 to 375	.0050	.0050	.0060	.0060	.0070	.0080	.0100	.0120	.0140	.0150
Copper, Brass, Bronze	75 to 200	75 to 250	.0050	.0050	.0060	.0060	.0070	.0080	.0100	.0120	.0140	.0150
Plastic	100 to 350	100 to 350	.0050	.0050	.0060	.0060	.0070	.0080	.0100	.0120	.0140	.0150

**Reamer Specifications:**  
 Cutting Diameter: +.0002 / -.0000  
 Shank Diameter: ±.0005  
 LOC: ±.030  
 OAL: ±.060  
 Helix (RH & LH): 12°  
 Lead Angle: 45°



**Total Stock Removal:**  
 Minimum and Maximum amounts of stock removal should be adhered to for proper reaming action. This is the amount the reamer should be oversized relative to the drilled hole.

Up to 1/16	.003 - .005
1/16 to 1/8	.004 - .008
1/8 to 1/4	.006 - .012
1/4 to 3/8	.008 - .014
3/8 to 1/2	.010 - .015
1/2 to 1"	.012 - .020

**TUNGSTEN  
 TOOLWORKS®.COM**